



Jampilen RCXP598

Random Copolymer

JAMPILen Polypropylene

Description:

"Jampilen RCXP598" is a medium modified random copolymer for the production of cast and blown films with reduced blooming effect. "Jampilen RCXP598" is formulated with a general purpose stabilization package and does not contain any slip- or antiblocking agents.

"Jampilen RCXP598" offers easy processability on both cast and water-quenched blown film lines. The mechanical properties of films made with "Jampilen RCXP598" are outstanding and the optical characteristics are superior to films made with conventional random copolymers. The seal initiation temperature is about 130°C and the blooming effect is minimal. Due to its good heat weldability, "Jampilen RCXP598" is suitable for monolayer films as well as sealing layers in coextruded films or laminated structures (e.g. with BOPP, PA, polyester or aluminum).

Processing Method:

Cast Film
Blown Film

Features:

Good mechanical properties
Good optical characteristics
Easy processability
Random copolymer

Typical Applications:

Monolayer films
Sealing layer in coextruded films or in laminated structures
Packaging of foodstuff and textiles
Stationery folders

Approval:

Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	9	g/10min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mechanical			
Flexural Modulus	1000	MPa	ASTM D790
Tensile Strength at Yield	28	MPa	ASTM D638
Tensile Elongation at Yield	13	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	50	J/m	ASTM D256
Rockwell Hardness	92	R Scale	ASTM D785
Thermal			
Vicat softening point (10N)	135	°C	ASTM D1525
H.D.T. (0.46 Mpa)	82	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	360	hours	ASTM D3012
Optical			
Haze	0.5	%	ASTM D1003
Gloss	88	----	ASTM D2457

4th Floor, No. 68, Taban St., Africa Blvd., Tehran, Iran.
Tel: +9821-84286, Fax: +9821-88879811
Email: info@jppc.ir
www.jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.