



Polypropylene H30S Fiber

Typical properties	Test method(ASTM)	Unit	Value
MFR @230°C, 2.16 kg	D1238/L	gr/10min	35
Felexural Modulus	D790	Mpa	1250
Notched Izod Impact@23°	CD256	J/m	34
Tensile Strength@Yield	D638	Mpa	30
Elongation@Yield	D638	%	11
Vicat Softening Point,10N	D1525	°C	152
HDT(0.46N/mm ²)	D648	°C	94
Oven Aging@150°C	D3012	Hours	360

➤ Values shown are averages & are not to be considered as product specifications.

❖ Main application & Characteristics:

H30S is a homo-polymer with High flow, medium MWD.

Application:

Fine denier cotton staple fiber, high speed short spinning operations. Coating of woven PP film yarn fabrics and paper coating. Injection moulding for household articles, toys and packaging.

Address:

No. 3, Taban St. Vali-e-Asr Ave. Tehran – IRAN **Tel:** (+98 21)82122700 **Fax:** (+98 21)8867 4126-27

Web-site: www.arpc.ir **E-mail:** Sales@arpc-ir.net