

Parslen ZRCT 230C

Parslen ZRCT 230C is a polypropylene random copolymer for pressure pipe systems with excellent heat resistance and superior toughness.

Parslen ZRCT 230C is a polypropylene-random-copolymer with an enhanced crystalline structure brought about by a special nucleation and with an improved temperature resistance. That exhibits excellent heat resistance and superior toughness.


In general Parslen ZRCT 230C is intended to be used in applications for plumbing and heating, such as in-house hot and cold water pipes and fittings, floor and wall heating systems and radiator connections.

Processing Method:

Pipe extrusion Sheet extrusion Injection molding of fitting

Features:

Higher Pressure resistance at high temperatures Superior toughness - Nucleated



Typical Applications:

Drinking water pipe Plumbing: Heating & Cooling Though sheets

| Typical properties | Unit | Value | Tolerance | Method |
|--|----------------|-------|------------|-------------------|
| Melt Flow Rate (230°C, 2.16kg) | g/10min | 0.35 | ± 0.05 | ASTM D1238 |
| Flexural Modulus | MPa | 900 | ± 100 | ASTM D790 |
| Tensile Strength at Yield | MPa | 25 | ± 3 | ASTM D638 |
| Tensile Elongation at Yield | % | 15 | ± 3 | ASTM D638 |
| Izod impact strength (notched) at 23°C | J/m | > 700 | - | ASTM D256 |
| Rockwell Hardness | R-Scale | 80 | + 10 | ASTM D785 |
| Vicat softening point | °C | 125 | ± 5 | ASTM D1525 |
| H.D.T. (0.45 MPa) | °C | 70 | ± 7 | ASTM D648 |

* These are typical property values not to be construed as exact product specification.

** All specimens are prepared by injection molding.