

PGPC2230

This is a kind of Polycarbonate polymer.

Applications: Suitable for injection modeling, Sports, Electrical, Automotive, Construction and Housing.

Analysis	Test Method	Condition	Unit	Guarantee Values
MFI (300°C)	ASTM D1238	1.2 Kg load	g/10 min	22.1
Density	ASTM D792	25 °C	g/cm ³	1.2
Tensile Strength	ASTM D638	@ yield	Mpa	≥ 60
Modulus of Elasticity	ASTM D638	---	Mpa	2000-2400
Elongation	ASTM D638	@ Break	%	≥ 50
Dielectric Strength	ASTM D149	@ 50 Hz	Kv/mm	≥ 18
Charpy Impact Strength	ASTM D6110	Notched	Kj/m ²	≥ 20
Vicat soft. Temp.	ASTM D1525	50 N , 50°C/h	°C	139-143
Transmittance	ASTM D1003	Thickness 2mm	%	≥ 80
Solvent Content	GC (int-st)	---	ppm	Max 1500
Yellow Index	ASTM D1925	PC-Granul	---	Max.6
	Pre-Drying			120°C/4hours